

POLYSHIELD 15



A 15-YEAR BUILT-UP WATERPROOFING SYSTEM

RUBBER-BASED TOP COAT/BASE COAT DEMONSTRATING OUTSTANDING CHARACTERISTICS, **SMOOTH**

Waterproofs roofs instantly – and keeps them waterproof for years to come

Polyshield 15 is a single pack, cold applied, rubber-based waterproofing coating for use as part of a reinforced built-up system. In conjunction with Polyshield Scrim it forms a fully-adhered, monolithic single-ply membrane for larger, all-over roofs where greater life expectancy is needed.

PERFORMANCE ADVANTAGES

- > Exceptional durability and performance of fifteen years
- > Cold applied - no hot works on roof
- > Unrivalled life cycle cost savings
- > Works instantly
- > A two-coat system developed for larger-all-over roofs where greater life expectancy is needed
- > Flexible, highly elastic solvent-based single pack coating with excellent adhesion to almost any wall or roof substrate
- > Rainfall immediately after application has no adverse effect
- > Excellent UV and resistance to movement of the substrate
- > Fast curing, can be applied at low temperatures

TESTS

Approvals/Standards:

- > External fire performance; BS 476-Part 3:2004 EXT.F.AC.
- > British Board of Agrément (BBA) Certificate:13/5042.



ENVIRONMENTAL IMPACT

- > Cold applied liquid roofing membranes have been recognised to help roofing elements achieve up to a BREEAM A+ rating (depending on the roof construction), demonstrating the sustainability and low environmental impact of this chemistry type.



USES

- > A built-up roof system for overlaying existing warm or cold roofs.
- > Flat Roofs, Pitched Roofs, Weathered Asphalt and Bituminous Surfaces, Gutters, Concrete, Brickwork, Fibreglass and GRP, Felted Surfaces, Asbestos Cladding, Sheetting and Guttering, Metal (Galvanised, Ferrous and Non-Ferrous), Old Lead, Previously Painted Surfaces* and Weathered Single-Ply membranes including EPDM*, PVC*, HYPALON*, TPO ROOF MEMBRANES* and PLASTISOL COATED SUBSTRATES*.
- *Adhesion/pull off test required.
- > Can be roller or brush applied.
- > Not for use on Walkways, Balconies, tanking, fish and aquatic ponds, new lead, Single Ply Membranes - Plasticised PVC (Plastisol) gutters, slate or internal use.

COLOUR RANGE

> **Basecoat:** Light Grey.

> **Topcoat:** Dark Grey.

BASECOAT/TOPCOAT PACK SIZE

> 5 and 20 litre containers.

SCRIM AVAILABILITY

> 1m x 100m, 0.5m x 100m, 0.2m x 50m rolls of Scrim available.

SUBSTRATE QUALITY

Cementitious substrates

New concrete should be cured for at least 28 days* and should have a pull off strength 1.5 N/mm². Inspect the concrete, including upstands, all areas should be hammer tested. Concrete must be suitably finished, preferably by wood float or steel pan. A power float finish is acceptable where the surface is prepared to avoid laitance (a tamped finish is not acceptable). The surface finish must be uniform and free from defects such as laitance, voids or honeycombing. The substrate must be of a suitable quality and condition to receive the system. Please refer to our Technical Department for further details.

Brick and stone

Bricks, blocks and mortar joints must be sound and preferably flush pointed.

Slates, tiles, etc.

Ensure all slates/tiles are sound and securely fastened, replacing obviously broken or missing sections

Asphalt

Asphalt contains volatiles which can cause bleeding and slight non-detrimental staining. The asphalt must be carefully assessed for moisture and/or air entrapment, grade and surface finish prior to any coating works being carried out

Bituminous felt

Ensure that bituminous felt is firmly adhered or mechanically fixed to the substrate. Bituminous felt should not contain any badly degraded areas.

Single ply

Single ply membranes must be correctly laid and securely fixed/adhered. Badly cracked or brittle membranes should be removed.

Bituminous coatings

Bituminous coatings should not have sticky or mobile surfaces, volatile mastic coatings, or old coal tar coatings.

Metals

Metals must be in sound condition

Timber substrates

Timber and timber based panel roof decks are to be well constructed, in good condition, firmly adhered, and with sufficient fixings for the nature and location of the site

Paints/Coatings

Ensure the existing material is sound and firmly adhered.

CLEANING OF SUBSTRATE

- > Clean the surface with a powerwash of up to 2,000 psi, depending on the substrate
- > If needed clean the area with Britannia Fungicidal Wash. This eliminates all moss/algae. The wash must be applied and left on the substrate for 7 days, then washed off prior to the application.
- > The substrate must be dried off using squeegees/rags. Gas guns should not be used.
- > Once the substrate is clean and dry you can then begin the application.

REPAIRS TO SUBSTRATE

Including splits, cracks, joints, seals and crazed areas.

- > Repair faults in the surface by using a high quality waterproof mastic/filler.
- > Apply Polyshield 15 system to repaired areas incorporating Britannia Reinforcing Scrim overlapping by 5cm.

GENERAL INSTALLATION

- > Installation must not be carried out during inclement weather (eg rain, fog or snow). When the temperature is below 5°C, suitable precautions against surface condensation on the substrate must be taken.
- > Substrates to which the system is to be applied must be sound, dry, clean and free from sharp projections such as nail heads and concrete nibs. Britannia's advice should be sought for suitable cleaning procedures and the use of a proprietary surface cleaner/fungicidal wash.
- > Previously coated areas must be checked for integrity and adequate adhesion to the substrate. Defects such as cracks and blisters must be repaired prior to application of the system in accordance with Britannia's instructions.
- > Adhesion checks should be carried out to ensure that the system is compatible with the existing surfaces and to determine the necessity for a primer.
- > Expansion or construction joints must be additionally reinforced prior to the application of the main waterproofing layer in accordance with Britannia's instructions.
- > Detailing, such as at upstands and penetrations, must be carried out in accordance with Britannia's instructions.

PRIMING

ALL ROOF SUBSTRATES REQUIRE PRIMING PRIOR TO OVERCOATING WITH THE POLYSHIELD 15 REINFORCED WATERPROOFING SYSTEM.

These surfaces should be cleaned prior to applying Polyshield 15 Reinforced Waterproofing System.

See Primer Guide for the following substrates:

Highly porous/friable surfaces

Felted surfaces, Concrete and asbestos cladding, sheeting and guttering should be primed with Britannia Polyshield Primer (see separate technical data sheet).

Concrete and masonry

Prime with Britannia Polyshield Primer.

OSB/Plywood and Wooden Substrates

OSB/Plywood, wooden substrates and insulation board must be treated with a 50mm wide strip of Britannia Tape (any other tape must be adhesion tested before use). A continuous surface should be created before commencing with the application of Britannia Polyshield Primer (see separate technical data sheet).

Weathered Single-Ply Membranes*

EPDM, PVC, HYPALON, TPO ROOF MEMBRANES and PLASTISOL COATED SUBSTRATES

Prime with Britannia Universal QD Primer-Sealer.

IT IS GOOD PRACTICE TO INSPECT AND CARRY OUT ADHESION TESTS ON THE SINGLE PLY MEMBRANES INCORPORATING PRIMER, DURASHIELD REINFORCED WATERPROOFING SYSTEM. BEFORE STARTING WORK PLEASE SEE THE SEPARATE ADHESION TEST DOCUMENT ON OUR WEBSITE.

Weathered asphalt and Bituminous surfaces

Prime with Britannia Polyshield Primer.

Note: discolouration may occur over a new asphalt, tar or bitumen surface. An extra coat may therefore be required for decorative purposes only. Aged bitumen can be liable to crack, therefore further advice should be taken.

Metal

All ferrous metals should be primed with Britannia Metal Primer (see separate technical data sheet).

Lead

No primer required on old lead, sheet/valleys.
DO NOT USE ON NEW LEAD.

Aluminium and Copper

Both of these should be primed with Britannia Two-Pack Self-Etching Primer (see separate technical data sheet).

Previously painted or coated substrates*

Prime with Britannia Polyshield Primer.

IT IS GOOD PRACTICE TO INSPECT AND CARRY OUT ADHESION TESTS ON ANY EXISTING COATING OR SUBSTRATE PRIOR TO APPLICATION OF THE COATING.

*Adhesion/pull off test required.



APPLICATION OF COATINGS

To a dry and cleaned surface:

- > Polyshield 15 Basecoat is applied by brush or roller to the clean prepared and primed substrate at a minimum of 1 litre per square metre.
- > Polyshield Reinforcing Scrim (100gm²) is embedded into the wet Polyshield 15 Basecoat avoiding creasing. Adjacent lengths of the reinforcement must overlap by a minimum of 75mm ensuring that there is sufficient coating to fully encapsulate the lap.
- > Polyshield 15 Topcoat is then applied by brush or roller over the dry, clean Polyshield 15 reinforced Basecoat at a minimum of 0.75 litres per square metre.
- > At each stage a check must be made for the presence of pinholes and missed areas, which can be rectified by applying additional coating as necessary.
- > Application rates for different substrate types are given in the table below.
- > **The substrate and ambient temperature for the application of the system must be between 2°C and 35°C.**

DO NOT APPLY to frozen or damp surfaces.
DO NOT APPLY in hot direct sunlight or coating may skin.

Spreading rate unreinforced over metal: 0.8 litres per square metre (includes both coats).

MINIMUM SPREADING RATES

	Basecoat /m ²	Topcoat/m ²
METAL SURFACES Unreinforced over Metal:		0.8 Lt
SMOOTH Asphalt, Carrier, Single Ply Membranes	1.0 Lt	0.75 Lt
INTERMEDIATE Worn Mineral Felt	1.25 Lt	0.75 Lt
ROUGH Heavy Mineralised Felt	1.5 Lt	1st 0.5 Lt 2nd 0.75 Lt

DRYING TIME

PRIMER

Britannia Polyshield Primer can take up to 1 day to cure but can be over coated when dry.

POLYSHIELD 15 BASECOAT

- > Surfaces must be COMPLETELY DRY prior to application of Polyshield 15 Basecoat.
- > Up to 8 hours or overnight depending on temperature and conditions.

POLYSHIELD 15 TOPCOAT

- > Surfaces must be COMPLETELY DRY prior to application of Polyshield 15 Topcoat.
- > Up to 8 hours or overnight depending on temperature and conditions.
- > Full cure: up to 7 days.
- > The product may remain slightly soft for a further period depending on climatic conditions, this is not detrimental to the waterproofing qualities of the product.

WATER REPELLENCY

- > Rainfall after application has no adverse effect.

CLEANING OF EQUIPMENT

- > For cleaning equipment use White Spirit.

SHELF LIFE

- > Up to two years if stored correctly in an unopened container.

PRECAUTIONS

- > **Flammable** keep away from sources of ignition.
- > Ensure good ventilation during application.
- > Wear gloves, goggles and suitable protective clothing.
- > In case of contact with eyes rinse immediately with plenty of water and seek medical advice.
- > Remove splashes from the skin with a recognised hand cleaner or plenty of soap and water.
- > Keep out of reach of children.
- > Do not use near fishponds.
- > Toxic to aquatic organisms. May cause long term adverse effects in the aquatic environments.
- > Do not empty into drains.

SAFETY

Good working practice should be followed and safety/walking boards should be utilised where required.

MAINTENANCE AND REPAIR

Maintenance

Roofs should be inspected at least annually in autumn after leaf fall to ensure vegetation and other debris is cleared from the roof and drainage outlets.

Repair

Any damage to the system must be repaired as soon as possible to ensure that waterproofing integrity is maintained.



Roller application

PRIMER GUIDE FOR POLYSHIELD 15 REINFORCED WATERPROOFING SYSTEM

Substrate	Britannia Polyshield FD Primer	Britannia Zinc Phosphate Metal Primer	Britannia 1 Pack Etching Primer	Britannia Universal QD Primer-Sealer
POROUS AND FRIABLE				
Felted Surfaces	✓			
Asbestos Cement	✓			
Concrete	✓			
Weathered Asphalt and Bituminous Surfaces	✓			
OSB/PLYWOOD AND WOODEN SUBSTRATES				
Timber Decks	✓			
Plywood	✓			
METALS				
Ferrous		✓		
Galvanised Metal			✓	
NON-FERROUS METALS				
Lead (not to be used on new lead)				
Aluminium			✓	
Copper			✓	
OTHERS				
Fibreglass and GRP	✓			
Previously painted or coated substrates*	✓			
EPDM*				✓
PVC*				✓
HYPALON*				✓
TPO ROOF MEMBRANES*				✓
PLASTISOL COATED SUBSTRATES*				✓

For difficult substrates and technical advice, please contact us

IT IS GOOD PRACTICE TO INSPECT AND CARRY OUT ADHESION TESTS INCORPORATING THE PRIMER AND POLYSHIELD. BEFORE STARTING WORK PLEASE SEE THE SEPARATE ADHESION TEST DOCUMENT ON OUR WEBSITE.

*Adhesion/pull off test required.

CLEANING OF EQUIPMENT

- > For cleaning equipment use White Spirit.

SHELF LIFE

- > Up to 2 years if stored correctly in an unopened container

PRECAUTIONS

- > **Flammable** keep away from sources of ignition.
- > Ensure good ventilation during application.
- > Wear gloves, goggles and suitable protective clothing.
- > In case of contact with eyes rinse immediately with plenty of water and seek medical advice.
- > Remove splashes from the skin with a recognised hand cleaner or plenty of soap and water.
- > Keep out of reach of children.
- > Do not use near fishponds.
- > Toxic to aquatic organisms. May cause long term adverse effects in the aquatic environments.
- > Do not empty into drains.

SAFETY

Good working practice should be followed and safety/walking boards should be utilised where required.

MAINTENANCE AND REPAIR

Maintenance

Roofs should be inspected at least annually in autumn after leaf fall to ensure vegetation and other debris is cleared from the roof and drainage outlets.

Repair

Any damage to the system must be repaired as soon as possible to ensure that waterproofing integrity is maintained.

IMPORTANT NOTES ON APPLICATION AND LIMITATIONS

- > Britannia Durashield is not recommended for the treatment of fish or aquatic ponds or internal use.
- > Air conditioning vents should be sealed for a minimum of 24 hours during and after the application.
- > **MINIMUM FINISHED FALL:** when using this product it is important that a minimum finished fall of 1:80 is achieved, as stated in BS 6229.2003 (Code of Practice for the application of Liquid Applied Waterproofing Systems to flat roofs with continuously supported coverings).
- > Do not apply Britannia Durashield on substrates with rising moisture.
- > Britannia Durashield is not suitable for permanent water immersion.
- > Do not dilute Britannia Durashield with any solvent.
- > On substrates likely to exhibit outgassing, apply during falling ambient and substrate temperatures. If applied during rising temperatures "pin holing" may occur from rising air.
- > Product should be used in conjunction with a safe system of work. Ensure an adequate assessment of all site risks has been conducted prior to work commencing. Refer to the product safety datasheet for further guidance.
- > Do not use Britannia Durashield for indoor applications
- > Do not apply close to the air intake vent of running air conditioning unit.
- > The product can be applied by brush or roller. Work well with a brush in difficult areas. Apply subsequent layers after the first layer has cured tack free.
- > Use strips of Britannia Reinforcing Scrim, in order to cover joints, connections or overlaps of bituminous sheets. Please ask our technical service department for detailed recommendations.
- > The suitability of each system to receive foot traffic varies. For specific recommendations, please contact our technical service department.
- > Do not apply adhesives or cementitious products (e.g. tile mortar) directly onto Durashield.
- > Do not use grit salt and/or other de-icing agents between coats of Durashield as this may affect the cure and inter-coat adhesion of the product.
- > Whilst Durashield is resistant to most commonly encountered atmospheric pollutants, proprietary cleaning solutions and environmental spoilage, the suitability of the product for use in applications with increased chemical resistance requirements should first be established in consultation with our technical service department.



THE BRITANNIA SERVICE

- > Nationwide sales and technical personnel.
- > Product warranties for approved contractors.
- > General specification reports/assistance.
- > Free on-site advice/surveys and technical reports.

THE BRITANNIA TRAINING CENTRE



**PLEASE CONTACT US
FOR FURTHER DETAILS
ON OUR APPROVED
CONTRACTOR PROGRAMME**



Certificate Number 8516
ISO 9001



Contact Details: Unit 7/8 King Street Trading Estate, Middlewich, Cheshire CW10 9LF
T: 01606 834015 F: 01606 837006 E: sales@britanniapaints.co.uk www.britanniapaints.co.uk

FURTHER INFORMATION

There is a Code of practice from LRWA-“Specification and use of Liquid Applied Waterproofing Systems” on www.lrwa.org.uk which can be consulted for general advice.

If in doubt regarding any of the above points, please contact our technical services department for advice.

A Material Safety Data Sheet is available on request.

It is the users responsibility to ensure that this data sheet is current prior to using the product.